Declaration of performance

Nr. 2023-006





| 1. | Product type | LOWIE DESIGN GREY HV HF |
|----|-----------------------------|--|
| 2. | Intended use | Masonry bricks by EN 771-3:20; EN 771-1_2011 |
| 3. | Name & address manufacturer | Lowie Bricks, Ropswalle 13 8930 Menen |
| 4. | Notified certification body | Procertus (identification number 0965) |

| 5. Declared performances | | |
|-----------------------------------|----------------|---------------|
| Essential features | Prestations | Test standard |
| Dimensions | 240X80X40 | EN_771-3_2011 |
| Flatness of facing sides | < 2,5 mm | EN_771-3_2011 |
| Flatness of bed sides | < 0,5 mm | EN_771-3_2011 |
| Planparallel bed sides | < 1 mm | EN_771-3_2011 |
| Mechanical strength after 14 days | > 10 N/mm2 | EN_771-3_2011 |
| Mechanical strength after 28 days | +- 20 N/mm2 | |
| Expansion/shrinkage | < 0,45 mm/m | EN_771-3_2011 |
| Insulation value (50/50) | 0,71 W/m*K | EN_771-3_2011 |
| Gross dry volume mass | 1690 KG/M3 | EN_771-3_2011 |
| Fire resistance | A1 | EN 13501-1 |
| Durability (freeze/thaw) | F2 | EN_771-1_2011 |
| Total water absorption | <16% | EN_771-1_2011 |
| Initial water absorption | < 4 kg/(m2min) | EN_771-1_2011 |

| Storage & Processing | Sawing |
|---|---|
| Flace on a narsunace and cover | Dry sawing may release dust. This dust will contain silicon or quartz particles that can be harmful to health. Anyone |
| Mix multiple packs | performing such work is advised to wear FFP3 dust masks. |
| Follow the Lowie Bricks processing instructions | |

Each pack contains 33% bricks with a painted header. These can be kept separate and used specifically in corner applications or locations where the header is visible.